

ZIRCONIA BALLS

Compressive Strength	794,837 psi
Maximum Useful Temperature	1800 °F
Thermal Conductivity	0.007 Cal/cm, Sec 0
Thermal Expansion	10.9 x 10 to the -6th power / °C
Electrical Resistivity	2.2 x 10 to the 12th power cm
Young's Modulus of Elasticity	30.6 x 10 to the 6th power, 21700 kgr/mm to the 2nd power
Hardness	1250 kgr/mm to the 2nd power
Density	.219 lbs/inch to the 3rd power